

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
14 February 2002 (14.02.2002)

PCT

(10) International Publication Number
WO 02/12151 A1

(51) International Patent Classification⁷: C07C 2/32

SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

(21) International Application Number: PCT/US01/24297

(22) International Filing Date: 3 August 2001 (03.08.2001)

(25) Filing Language: English

(26) Publication Language: English

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(30) Priority Data:
60/222,786 3 August 2000 (03.08.2000) US

Declaration under Rule 4.17:

— as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii)) for the following designations AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG)

(71) Applicant (*for all designated States except US*): E.I. DUPONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US).

(72) Inventor; and

(75) Inventor/Applicant (*for US only*): SCHIFFINO, Rinaldo, S. [US/US]; 4809 Threadneedle Road, Wilmington, DE 19807 (US).

(74) Agent: LERMAN, Bart, E.; E.I. Dupont de Nemours and Company, Legal Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US).

Published:

— with international search report

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK,

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: CONTINUOUS MANUFACTURING PROCESS FOR α -OLEFINS

(57) Abstract: A manufacturing process for α -olefins using certain iron containing ethylene oligomerization catalysts together with alkylaluminum cocatalysts, in which using a low ratio of Al:Fe in the process results in a lowered formation of undesired polyethylene waxes and polymer. This results in less fouling of the process lines and vessels in the manufacturing plant.

WO 02/12151 A1

TITLECONTINUOUS MANUFACTURING PROCESS FOR α -OLEFINSFIELD OF THE INVENTION

A continuous manufacturing process for α -olefins using certain iron containing ethylene oligomerization catalysts together with alkylaluminum cocatalysts, in which using a low ratio of Al:Fe in the process results in a lowered formation of undesired polyethylene waxes and polymer.

TECHNICAL BACKGROUND

α -Olefins are important items of commerce, billions of kilograms being manufactured yearly. They are useful as monomers for (co)polymerizations and as chemical intermediates for the manufacture of many other materials, for example detergents and surfactants. Presently most α -olefins are made by the catalyzed oligomerization of ethylene by various catalysts, especially certain nickel complexes or aluminum alkyls, see for instance US4020121 and I. Kroschwitz, et al., Ed., Kirk-Othmer Encyclopedia of Chemical Technology, 4th Ed., Vol. 17, John Wiley & Sons, New York, p 839-858.

Recently, as reported in US5955555 and US6103946, both of which are hereby incorporated by reference herein for all purposes as if fully set forth, it has been found that iron complexes of certain tridentate ligands are excellent catalysts for the production of α -olefins from ethylene. Among the options for using such catalysts are those in which the iron complexes are used in conjunction with a cocatalyst, particularly an alkylaluminum cocatalyst such as an alkylaluminumoxane.


It has recently been found, particularly in continuous processes using such iron complexes, that high molar ratios of Al:Fe lead to the undesirable formation of polyethylene waxes and polymers, which tend to foul the oligomerization

apparatus. It has now been found that lower Al:Fe ratios diminish the formation of these undesirable polyethylenes, while not otherwise significantly deleteriously affecting the process.

SUMMARY OF THE INVENTION

This invention concerns a method for reducing the formation of polyethylene waxes and polymers in a continuous process for the production of a linear α -olefin product, said continuous process comprising the step of contacting, in a continuous reactor, process ingredients comprising an ethylene oligomerization catalyst composition, ethylene and a cocatalyst, wherein:

(a) the ethylene oligomerization catalyst composition comprises an iron complex of a compound of the formula



wherein:

R^1 , R^2 and R^3 are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl or an inert functional group, provided that any two of R^1 , R^2 and R^3 vicinal to one another taken together may form a ring;

R^4 and R^5 are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl or an inert functional group;

R^6 and R^7 are each independently a substituted aryl having a first ring atom bound to the imino nitrogen, provided that:

in R^6 , a second ring atom adjacent to said first ring atom is bound to a halogen, a primary carbon group, a secondary carbon group or a tertiary carbon group; and further provided that

in R⁶, when said second ring atom is bound to a halogen or a primary carbon group, none, one or two of the other ring atoms in R⁶ and R⁷ adjacent to said first ring atom are bound to a halogen or a primary carbon group, with the remainder of the ring atoms adjacent to said first ring atom being bound to a hydrogen atom; or

in R⁶, when said second ring atom is bound to a secondary carbon group, none, one or two of the other ring atoms in R⁶ and R⁷ adjacent to said first ring atom are bound to a halogen, a primary carbon group or a secondary carbon group, with the remainder of the ring atoms adjacent to said first ring atom being bound to a hydrogen atom; or

in R⁶, when said second ring atom is bound to a tertiary carbon group, none or one of the other ring atoms in R⁶ and R⁷ adjacent to said first ring atom are bound to a tertiary carbon group, with the remainder of the ring atoms adjacent to said first ring atom being bound to a hydrogen atom; and

(b) the cocatalyst comprises an alkyl aluminum compound;


said method for reducing comprising the step of contacting said process ingredients in amounts such that the molar ratio of Al in the cocatalyst to Fe in the ethylene oligomerization catalyst is about 2000 or less.

Stated another way, the present invention concerns the use, in the aforementioned continuous process, of a molar ratio of Al in the cocatalyst to Fe in the ethylene oligomerization catalyst is about 2000 or less, to reduce the formation of polyethylene waxes and polymers in such a continuous process.

The present invention also concerns a continuous process for the production of a linear α -olefin product, the process comprising the step of contacting, in a continuous reactor, process ingredients comprising an ethylene oli-

gomerization catalyst composition, ethylene and a cocatalyst, wherein:

(a) the ethylene oligomerization catalyst composition comprises an iron complex of a compound of the formula



wherein:

R^1 , R^2 and R^3 are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl or an inert functional group, provided that any two of R^1 , R^2 and R^3 vicinal to one another taken together may form a ring;

R^4 and R^5 are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl or an inert functional group;

R^6 and R^7 are each independently a substituted aryl having a first ring atom bound to the imino nitrogen, provided that:

in R^6 , a second ring atom adjacent to said first ring atom is bound to a halogen, a primary carbon group, a secondary carbon group or a tertiary carbon group; and further provided that

in R^6 , when said second ring atom is bound to a halogen or a primary carbon group, none, one or two of the other ring atoms in R^6 and R^7 adjacent to said first ring atom are bound to a halogen or a primary carbon group, with the remainder of the ring atoms adjacent to said first ring atom being bound to a hydrogen atom; or

in R^6 , when said second ring atom is bound to a secondary carbon group, none, one or two of the other ring atoms in R^6 and R^7 adjacent to said first ring atom are bound to a

halogen, a primary carbon group or a secondary carbon group, with the remainder of the ring atoms adjacent to said first ring atom being bound to a hydrogen atom; or

in R⁶, when said second ring atom is bound to a tertiary carbon group, none or one of the other ring atoms in R⁶ and R⁷ adjacent to said first ring atom are bound to a tertiary carbon group, with the remainder of the ring atoms adjacent to said first ring atom being bound to a hydrogen atom; and

(b) the cocatalyst comprises an alkyl aluminum compound;

characterized in that the molar ratio of Al in the cocatalyst to Fe in the ethylene oligomerization catalyst is from about 5 to about 300.

These and other features and advantages of the present invention will be more readily understood by those of ordinary skill in the art from a reading of the following detailed description. It is to be appreciated that certain features of the invention which are, for clarity, described below in the context of separate embodiments, may also be provided in combination in a single embodiment. Conversely, various features of the invention which are, for brevity, described in the context of a single embodiment, may also be provided separately or in any subcombination.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

Herein, certain terms are used. Some of them are:

A "hydrocarbyl group" is a univalent group containing only carbon and hydrogen. As examples of hydrocarbyls may be mentioned unsubstituted alkyls, cycloalkyls and aryls. If not otherwise stated, it is preferred that hydrocarbyl groups (and alkyl groups) herein contain 1 to about 30 carbon atoms.

By "substituted hydrocarbyl" herein is meant a hydrocarbyl group that contains one or more substituent groups

which are inert under the process conditions to which the compound containing these groups is subjected (e.g., an inert functional group, see below). The substituent groups also do not substantially detrimentally interfere with the oligomerization process or operation of the oligomerization catalyst system. If not otherwise stated, it is preferred that substituted hydrocarbyl groups herein contain 1 to about 30 carbon atoms. Included in the meaning of "substituted" are rings containing one or more heteroatoms, such as nitrogen, oxygen and/or sulfur, and the free valence of the substituted hydrocarbyl may be to the heteroatom. In a substituted hydrocarbyl, all of the hydrogens may be substituted, as in trifluoromethyl.

By "(inert) functional group" herein is meant a group, other than hydrocarbyl or substituted hydrocarbyl, which is inert under the process conditions to which the compound containing the group is subjected. The functional groups also do not substantially deleteriously interfere with any process described herein that the compound in which they are present may take part in. Examples of functional groups include halo (fluoro, chloro, bromo and iodo), and ether such as $-OR^{50}$ wherein R^{50} is hydrocarbyl or substituted hydrocarbyl. In cases in which the functional group may be near a transition metal (Fe) atom, the functional group alone should not coordinate to the metal atom (Fe) more strongly than the groups in those compounds that are shown as coordinating to the metal atom, that is they should not displace the desired coordinating group.


By a "cocatalyst" or a "catalyst activator" is meant one or more compounds that react with a transition metal compound to form an activated catalyst species. One such catalyst activator is an "alkyl aluminum compound" which, herein, is meant a compound in which at least one alkyl

group is bound to an aluminum atom. Other groups such as, for example, alkoxide, hydride and halogen may also be bound to aluminum atoms in the compound.

By a "linear α -olefin product" is meant a composition predominantly comprising a compound (or mixture of compounds) of the formula $H(CH_2CH_2)_qCH=CH_2$ wherein q is an integer of 1 to about 18. In most cases, the linear α -olefin product of the present process will be a mixture of compounds having differing values of q of from 1 to 18, with a minor amount of compounds having q values of more than 18. Preferably less than 50 weight percent, and more preferably less than 20 weight percent, of the product will have q values over 18. The product may further contain small amounts (preferably less than 30 weight percent, more preferably less than 10 weight percent, and especially preferably less than 2 weight percent) of other types of compounds such as alkanes, branched alkenes, dienes and/or internal olefins.


By a "primary carbon group" herein is meant a group of the formula $-CH_2---$, wherein the free valence $---$ is to any other atom, and the bond represented by the solid line is to a ring atom of a substituted aryl to which the primary carbon group is attached. Thus the free valence $---$ may be bonded to a hydrogen atom, a halogen atom, a carbon atom, an oxygen atom, a sulfur atom, etc. In other words, the free valence $---$ may be to hydrogen, hydrocarbyl, substituted hydrocarbyl or a functional group. Examples of primary carbon groups include $-CH_3$, $-CH_2CH(CH_3)_2$, $-CH_2Cl$, $-CH_2C_6H_5$, $-OCH_3$ and $-CH_2OCH_3$.

By a "secondary carbon group" is meant the group



wherein the bond represented by the solid line is to a ring atom of a substituted aryl to which the secondary carbon group is attached, and both free bonds represented by the dashed lines are to an atom or atoms other than hydrogen. These atoms or groups may be the same or different. In other words the free valences represented by the dashed lines may be hydrocarbyl, substituted hydrocarbyl or inert functional groups. Examples of secondary carbon groups include $-\text{CH}(\text{CH}_3)_2$, $-\text{CHCl}_2$, $-\text{CH}(\text{C}_6\text{H}_5)_2$, cyclohexyl, $-\text{CH}(\text{CH}_3)\text{OCH}_3$, and $-\text{CH}=\text{CCH}_3$.

By a "tertiary carbon group" is meant a group of the formula




wherein the bond represented by the solid line is to a ring atom of a substituted aryl to which the tertiary carbon group is attached, and the three free bonds represented by the dashed lines are to an atom or atoms other than hydrogen. In other words, the bonds represented by the dashed lines are to hydrocarbyl, substituted hydrocarbyl or inert functional groups. Examples of tertiary carbon groups include $-\text{C}(\text{CH}_3)_3$, $-\text{C}(\text{C}_6\text{H}_5)_3$, $-\text{CCl}_3$, $-\text{CF}_3$, $-\text{C}(\text{CH}_3)_2\text{OCH}_3$, $-\text{C}\equiv\text{CH}$, $-\text{C}(\text{CH}_3)_2\text{CH}=\text{CH}_2$, aryl and substituted aryl such as phenyl and 1-adamantyl.

By "aryl" is meant a monovalent aromatic group in which the free valence is to the carbon atom of an aromatic ring. An aryl may have one or more aromatic rings which may be fused, connected by single bonds or other groups.


By "substituted aryl" is meant a monovalent aromatic group substituted as set forth in the above definition of "substituted hydrocarbyl". Similar to an aryl, a substituted aryl may have one or more aromatic rings which may be

fused, connected by single bonds or other groups; however, when the substituted aryl has a heteroaromatic ring, the free valence in the substituted aryl group can be to a heteroatom (such as nitrogen) of the heteroaromatic ring instead of a carbon.


By a "first ring atom in R^6 and R^7 bound to an imino nitrogen atom" is meant the ring atom in these groups bound to an imino nitrogen shown in (I), for example




the atoms shown in the 1-position in the rings in (II) and (III) are the first ring atoms bound to an imino carbon atom (other groups which may be substituted on the aryl groups are not shown). Ring atoms adjacent to the first ring atoms are shown, for example, in (IV) and (V), where the open valencies to these adjacent atoms are shown by dashed lines (the 2,6-positions in (IV) and the 2,5-positions in (V)).



In one preferred compound (I) R^6 is



and R^7 is



(VII)

wherein:

R^8 is a halogen, a primary carbon group, a secondary carbon group or a tertiary carbon group; and

R^9 , R^{10} , R^{11} , R^{14} , R^{15} , R^{16} and R^{17} are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl or a functional group;

provided that:

when R^8 is a halogen or primary carbon group none, one or two of R^{12} , R^{13} and R^{17} are a halogen or a primary carbon group, with the remainder of R^{12} , R^{13} and R^{17} being hydrogen; or

when R^8 is a secondary carbon group, none or one of R^{12} , R^{13} and R^{17} is a halogen, a primary carbon group or a secondary carbon group, with the remainder of R^{12} , R^{13} and R^{17} being hydrogen; or

when R^8 is a tertiary carbon group, none or one of R^{12} , R^{13} and R^{17} is tertiary carbon group, with the remainder of R^{12} , R^{13} and R^{17} being hydrogen;

and further provided that any two of R^8 , R^9 , R^{10} , R^{11} , R^{12} , R^{13} , R^{14} , R^{15} , R^{16} and R^{17} vicinal to one another, taken together may form a ring.

In the above formulas (VI) and (VII), R^8 corresponds to the second ring atom adjacent to the first ring atom bound to the imino nitrogen, and R^{12} , R^{13} and R^{17} correspond to the other ring atoms adjacent to the first ring atom.

In compounds (I) containing (VI) and (VII), it is particularly preferred that:

if R^8 is a primary carbon group, R^{13} is a primary carbon group, and R^{12} and R^{17} are hydrogen; or

if R^8 is a secondary carbon group, R^{13} is a primary carbon group or a secondary carbon group, more preferably a secondary carbon group, and R^{12} and R^{17} are hydrogen; or

if R^8 is a tertiary carbon group (more preferably a trihalo tertiary carbon group such as a trihalomethyl), R^{13} is a tertiary carbon group (more preferably a trihalotertiary group such as a trihalomethyl), and R^{12} and R^{17} are hydrogen; or

if R^8 is a halogen, R^{13} is a halogen, and R^{12} and R^{17} are hydrogen.

In all specific preferred compounds (I) in which (VI) and (VII) appear, it is preferred that R^1 , R^2 and R^3 are hydrogen; and/or R^4 and R^5 are methyl. It is further preferred that:

R^9 , R^{10} , R^{11} , R^{12} , R^{14} , R^{15} , R^{16} and R^{17} are all hydrogen; R^{13} is methyl; and R^8 is a primary carbon group, more preferably methyl; or

R^9 , R^{10} , R^{11} , R^{12} , R^{14} , R^{15} , R^{16} and R^{17} are all hydrogen; R^{13} is ethyl; and R^8 is a primary carbon group, more preferably ethyl; or


R^9 , R^{10} , R^{11} , R^{12} , R^{14} , R^{15} , R^{16} and R^{17} are all hydrogen; R^{13} is isopropyl; and R^8 is a primary carbon group, more preferably isopropyl; or

R^9 , R^{10} , R^{11} , R^{12} , R^{14} , R^{15} , R^{16} and R^{17} are all hydrogen; R^{13} is n-propyl; and R^8 is a primary carbon group, more preferably n-propyl; or

R^9 , R^{10} , R^{11} , R^{12} , R^{14} , R^{15} , R^{16} and R^{17} are all hydrogen; R^{13} is chloro; and R^8 is a halogen, more preferably chloro; or

R^9 , R^{10} , R^{11} , R^{12} , R^{14} , R^{15} , R^{16} and R^{17} are all hydrogen; R^{13} is trihalomethyl, more preferably trifluoromethyl; and R^8 is a trihalomethyl, more preferably trifluoromethyl.

In another preferred embodiment of (I), R^6 and R^7 are, respectively



wherein:

R^{18} is a halogen, a primary carbon group, a secondary carbon group or a tertiary carbon group; and

R^{19} , R^{20} , R^{23} and R^{24} are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl or a functional group;

Provided that:

when R^{18} is a halogen or primary carbon group none, one or two of R^{21} , R^{22} and R^{25} are a halogen or a primary carbon group, with the remainder of R^{21} , R^{22} and R^{25} being hydrogen; or

when R^{18} is a secondary carbon group, none or one of R^{21} , R^{22} and R^{25} is a halogen, a primary carbon group or a secondary carbon group, with the remainder of R^{21} , R^{22} and R^{25} being hydrogen;

when R^{18} is a tertiary carbon group, none or one of R^{21} , R^{22} and R^{25} is a tertiary carbon group, with the remainder of R^{21} , R^{22} and R^{25} being hydrogen;

and further provided that any two of R^{18} , R^{19} , R^{20} , R^{21} , R^{22} , R^{23} , R^{24} and R^{25} vicinal to one another, taken together may form a ring.

In the above formulas (VIII) and (IX), R^{18} corresponds to the second ring atom adjacent to the first ring atom

bound to the imino nitrogen, and R^{21} , R^{22} and R^{25} correspond to the other ring atoms adjacent to the first ring atom.

In compounds (I) containing (VIII) and (IX), it is particularly preferred that:

if R^{18} is a primary carbon group, R^{22} is a primary carbon group, and R^{21} and R^{25} are hydrogen; or

if R^{18} is a secondary carbon group, R^{22} is a primary carbon group or a secondary carbon group, more preferably a secondary carbon group, and R^{21} and R^{25} are hydrogen; or

if R^{18} is a tertiary carbon group (more preferably a trihalo tertiary carbon group such as a trihalomethyl), R^{22} is a tertiary carbon group (more preferably a trihalotertiary group such as a trihalomethyl), and R^{21} and R^{25} are hydrogen; or

if R^{18} is a halogen, R^{22} is a halogen, and R^{21} and R^{25} are hydrogen.

In all specific preferred compounds (I) in which (VIII) and (IX) appear, it is preferred that R^1 , R^2 and R^3 are hydrogen; and/or R^4 and R^5 are methyl. It is further preferred that:

R^{19} , R^{20} , R^{21} , R^{23} and R^{24} are all hydrogen; R^{22} is methyl; and R^{18} is a primary carbon group, more preferably methyl; or

R^{19} , R^{20} , R^{21} , R^{23} and R^{24} are all hydrogen; R^{22} is ethyl; and R^{18} is a primary carbon group, more preferably ethyl; or

R^{19} , R^{20} , R^{21} , R^{23} and R^{24} are all hydrogen; R^{22} is isopropyl; and R^{18} is a primary carbon group, more preferably isopropyl; or

R^{19} , R^{20} , R^{21} , R^{23} and R^{24} are all hydrogen; R^{22} is n-propyl; and R^{18} is a primary carbon group, more preferably n-propyl; or

R^{19} , R^{20} , R^{21} , R^{23} and R^{24} are all hydrogen; R^{22} is chloro or bromo; and R^{18} is a halogen, more preferably chloro or bromo.

Compound (I) and its iron complexes (the oligomerization catalyst) may be prepared by a variety of methods, see for instance previously incorporated US5955555 and US6103946, as well as US6232259 and W000/08034, both of which are also incorporated by reference herein for all purposes as if fully set forth.

It is preferred herein to react an iron complex of (I), such as a complex of (I) with FeCl_2 , with the cocatalyst (e.g., the alkylaluminum compound), preferably an aluminoxane such as methylaluminumoxane, to form an active ethylene oligomerization species. The molar ratio of aluminum (as alkylaluminum compound) to iron (as a complex) in the oligomerization preferably is about 2000 or less. A more preferred upper limit is about 1500 or less, still more preferably about 1000 or less, and especially about 700 or less; and as a lower limit is about 5 or more, more preferably about 10 or more, still more preferably about 100 or more, even more preferably about 300 or more, and especially about 500 or more. For clarity, any combination of the aforementioned upper and lower limits may be used to define a preferred range herein such as, for example, from about 5 to about 1500, from about 5 to about 1000, from about 100 to about 1000, from about 500 to about 700, and other such combination.

Another preferred range in accordance with the present invention is from about 5 to about 300. Within this range, a more preferred lower limit is about 10 or more, more preferably about 20 or more, still more preferably about 30 or more, and especially about 50 or more; and a more preferred upper limit about 200 or less, still more preferably about 150 or less, and especially about 100 or less. Again for clarity, any combination of the aforementioned upper and lower limits may be used to define a preferred range herein.

It should be noted that the above ranges refer to steady state operating conditions. Under certain circumstances, it may be beneficial to start the reaction under higher Al:Fe ratios then, in the course of the process stabilizing, lower the Al:Fe ratio to the desired steady state level. For example, the reaction could be started at above any of the upper ratio limits mentioned above, then reduced to the desired level at or above any of the lower ratio limits mentioned above.

Preferred alkylaluminum compounds include one or more of R^{51}_3Al , $R^{51}AlCl_2$, R^{51}_2AlCl , and " $R^{51}AlO$ " (alkylaluminumoxanes), wherein R^{51} is alkyl containing 1 to 25 carbon atoms, preferably 1 to 4 carbon atoms. Specific alkylaluminum compounds include methylaluminumoxane (which is an oligomer with the general formula $(MeAlO)_n$), $(C_2H_5)_2AlCl$, $C_2H_5AlCl_2$, $(C_2H_5)_3Al$ and $((CH_3)_2CHCH_2)_3Al$. A preferred alkylaluminum compound is an aluminumoxane, especially methyl aluminumoxane.

The conditions for the oligomerization described in previously incorporated US6103946 and United States Appl. Ser. No. 09/906,974 (filed July 17, 2001), entitled "MANUFACTURING PROCESS FOR ALPHA-OLEFINS" (corresponding to PCT Appln. PCT/US01/22628, filed July 18, 2001), may otherwise be followed.

For example, the oligomerization reaction may be run at a wide range of temperatures generally ranging from about $-100^\circ C$ to about $+300^\circ C$, preferably about $0^\circ C$ to about $200^\circ C$, and more preferably about $20^\circ C$ to about $100^\circ C$. Pressures may also vary widely, ranging from an ethylene pressure (gauge) of from about 0 kPa to about 35 MPa, more preferably from about 500 kPa to about 15 MPa.

The process may be run in gas or liquid phase, but is typically run in liquid phase, preferably using an aprotic organic liquid. The process ingredients and products may or

may not be soluble in these liquids, but obviously these liquids should not prevent the oligomerization from occurring. Suitable liquids include alkanes, alkenes, cycloalkanes, selected halogenated hydrocarbons and aromatic hydrocarbons. Specific useful liquids include hexane, toluene, benzene and the α -olefins themselves.

The ethylene oligomerizations herein may also initially be carried out in the solid state by, for instance, supporting and active catalyst and/or aluminum compound on a substrate such as silica or alumina. Alternatively a solution of the catalyst precursor may be exposed to a support having an alkylaluminum compound on its surface. These "heterogeneous" catalysts may be used to catalyze oligomerization in the gas phase or the liquid phase. By "gas phase" is meant that the ethylene is transported to contact with the catalyst particle while the ethylene is in the gas phase. In general, the oligomerization may be run as a continuous gas phase, solution or slurry processes.

It is particularly preferred to run the oligomerization as "essentially single phase liquid full", which means that at least 95 volume percent of the reactor volume is occupied by a liquid that is a single phase. Small amounts of the reactor volume may be taken up by gas, for example ethylene may be added to the reactor as a gas, which dissolves rapidly under the process conditions. Nevertheless, some small amount of dissolving ethylene gas may be present. Not counted in the reactor volume is any solid resulting from fouling of the reactor. See, for example, previously incorporated United States Appl. Ser. No. 09/ Ser. No. 09/906,974 (filed July 17, 2001), entitled "MANUFACTURING PROCESS FOR ALPHA-OLEFINS" (corresponding to PCT Appln. PCT/US01/22628, filed July 18, 2001).

These molar ratios of Al:Fe described herein are based on the process ingredients, that is, the ingredients comprising the reactor feed; therefore, it is preferred at such low molar Al:Fe ratios to purify the process ingredients so that the alkylaluminum compounds are not "used up" reacting with moisture or other impurities.

Using the oligomerization catalysts described herein a mixture of α -olefins is obtained. A measure of the molecular weights of the olefins obtained is factor K from the Schulz-Flory theory (see for instance B. Elvers, et al., Ed. Ullmann's Encyclopedia of Industrial Chemistry, Vol. A13, VCH Verlagsgesellschaft mbH, Weinheim, 1989, p. 243-247 and 275-276). This is defined as:

$$K = n(C_{n+2} \text{ olefin}) / n(C_n \text{ olefin})$$


wherein $n(C_n \text{ olefin})$ is the number of moles of olefin containing n carbon atoms, and $n(C_{n+2} \text{ olefin})$ is the number of moles of olefin containing n+2 carbon atoms, or in other words the next higher oligomer of C_n olefin. From this can be determined the weight (mass) fractions of the various olefins in the resulting oligomeric reaction product mixture. The K factor is preferred to be in the range of about 0.65 to about 0.8 to make the α -olefins of the most commercial interest. This factor can be varied to some extent, see for instance previously incorporated US6103946 and United States Appln. Ser. No. 09/906,974 (filed July 17, 2001), entitled "MANUFACTURING PROCESS FOR ALPHA-OLEFINS" (corresponding to PCT Appln. PCT/US01/22628, filed July 18, 2001).

CLAIMS

What is claimed is:

1. A method for reducing the formation of polyethylene waxes and polymers in a continuous process for the production of a linear α -olefin product, said continuous process comprising the step of contacting, in a continuous reactor, process ingredients comprising an ethylene oligomerization catalyst composition, ethylene and a cocatalyst, wherein:

(a) the ethylene oligomerization catalyst composition comprises an iron complex of a compound of the formula



wherein:

R^1 , R^2 and R^3 are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl or an inert functional group, provided that any two of R^1 , R^2 and R^3 vicinal to one another taken together may form a ring;

R^4 and R^5 are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl or an inert functional group;

R^6 and R^7 are each independently a substituted aryl having a first ring atom bound to the imino nitrogen, provided that:

in R^6 , a second ring atom adjacent to said first ring atom is bound to a halogen, a primary carbon group, a secondary carbon group or a tertiary carbon group; and further provided that

in R^6 , when said second ring atom is bound to a halogen or a primary carbon group, none, one or two of the other ring atoms in R^6 and R^7 adjacent to said first ring atom are bound to a halogen or a primary carbon group, with the re-

remainder of the ring atoms adjacent to said first ring atom being bound to a hydrogen atom; or

in R⁶, when said second ring atom is bound to a secondary carbon group, none, one or two of the other ring atoms in R⁶ and R⁷ adjacent to said first ring atom are bound to a halogen, a primary carbon group or a secondary carbon group, with the remainder of the ring atoms adjacent to said first ring atom being bound to a hydrogen atom; or

in R⁶, when said second ring atom is bound to a tertiary carbon group, none or one of the other ring atoms in R⁶ and R⁷ adjacent to said first ring atom are bound to a tertiary carbon group, with the remainder of the ring atoms adjacent to said first ring atom being bound to a hydrogen atom; and

(b) the cocatalyst comprises an alkyl aluminum compound;

said method for reducing comprising the step of contacting said process ingredients in amounts such that the molar ratio of Al in the cocatalyst to Fe in the ethylene oligomerization catalyst is about 2000 or less.

2. The method of claim 1, wherein said molar ratio is from about 100 to about 1500.

3. The method of claim 1, wherein said molar ratio is from about 300 to about 1000.

4. The method of claim 1, wherein said molar ratio is from about 500 to about 700.


5. The method of claim 1, wherein said molar ratio is from about 5 to about 300.

6. The method of claim 1, wherein the continuous reactor is essentially single phase liquid full.

7. A continuous process for the production of a linear α -olefin product, the process comprising the step of contacting, in a continuous reactor, process ingredients com-

prising an ethylene oligomerization catalyst composition, ethylene and a cocatalyst, wherein:

(a) the ethylene oligomerization catalyst composition comprises an iron complex of a compound of the formula



wherein:

R^1 , R^2 and R^3 are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl or an inert functional group, provided that any two of R^1 , R^2 and R^3 vicinal to one another taken together may form a ring;

R^4 and R^5 are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl or an inert functional group;

R^6 and R^7 are each independently a substituted aryl having a first ring atom bound to the imino nitrogen, provided that:

in R^6 , a second ring atom adjacent to said first ring atom is bound to a halogen, a primary carbon group, a secondary carbon group or a tertiary carbon group; and further provided that

in R^6 , when said second ring atom is bound to a halogen or a primary carbon group, none, one or two of the other ring atoms in R^6 and R^7 adjacent to said first ring atom are bound to a halogen or a primary carbon group, with the remainder of the ring atoms adjacent to said first ring atom being bound to a hydrogen atom; or

in R^6 , when said second ring atom is bound to a secondary carbon group, none, one or two of the other ring atoms in R^6 and R^7 adjacent to said first ring atom are bound to a

halogen, a primary carbon group or a secondary carbon group, with the remainder of the ring atoms adjacent to said first ring atom being bound to a hydrogen atom; or

in R^6 , when said second ring atom is bound to a tertiary carbon group, none or one of the other ring atoms in R^6 and R^7 adjacent to said first ring atom are bound to a tertiary carbon group, with the remainder of the ring atoms adjacent to said first ring atom being bound to a hydrogen atom; and

(b) the cocatalyst comprises an alkyl aluminum compound;

characterized in that the molar ratio of Al in the cocatalyst to Fe in the ethylene oligomerization catalyst is from about 5 to about 300.

8. The process of claim 7, wherein the continuous reactor is essentially single phase liquid full.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 01/24297

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 C07C2/32

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C07C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 98 27124 A (E.I. DU PONT DE NEMOURS) 25 June 1998 (1998-06-25) claims	1
A	US 5 955 555 A (BENNETT ALISON MARGARET ANNE) 21 September 1999 (1999-09-21) cited in the application claims	1
A	WO 00 15646 A (BP CHEMICALS) 23 March 2000 (2000-03-23) claims	1

☐ Further documents are listed in the continuation of box C.

Patent family members are listed in annex.

* Special categories of cited documents:

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

Z document member of the same patent family

Date of the actual completion of the international search

15 November 2001

Date of mailing of the international search report

23/11/2001

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Van Geyt, J

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No
PCT/US 01/24297

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9827124	A	25-06-1998	AU 735653 B2	12-07-2001
			AU 5711098 A	15-07-1998
			BR 9714219 A	18-04-2000
			EP 1127897 A2	29-08-2001
			EP 0946609 A1	06-10-1999
			HU 0000031 A2	28-05-2000
			JP 2000516295 T	05-12-2000
			NO 992930 A	10-08-1999
			PL 334300 A1	14-02-2000
			TR 9901352 T2	21-10-1999
			WO 9827124 A1	25-06-1998
			US 6214761 B1	10-04-2001
			US 2001000519 A1	26-04-2001
			US 5955555 A	21-09-1999
US 5955555	A	21-09-1999	US 6214761 B1	10-04-2001
			US 2001000519 A1	26-04-2001
			AU 735653 B2	12-07-2001
			AU 5711098 A	15-07-1998
			BR 9714219 A	18-04-2000
			EP 1127897 A2	29-08-2001
			EP 0946609 A1	06-10-1999
			HU 0000031 A2	28-05-2000
			JP 2000516295 T	05-12-2000
			NO 992930 A	10-08-1999
			PL 334300 A1	14-02-2000
			TR 9901352 T2	21-10-1999
			WO 9827124 A1	25-06-1998
WO 0015646	A	23-03-2000	AU 5637899 A	03-04-2000
			EP 1123303 A1	16-08-2001
			WO 0015646 A1	23-03-2000